



TECHNICAL DATA SHEET No 835

## SPRAY P961 ETCH PRIMER

### GENERAL TECHNICAL DESCRIPTION

Fast drying 1K adhesion promoter primer for all metallic surfaces.

Paintable with all 1K and 2K primers and topcoats.

Available in a variety of shades that can simulate E-COAT and OEM inner parts colours (e.g. inside trunk area).

### SURFACE

Aluminium  
Stainless steel  
Galvanised  
Bare steel  
Chrome

### PRETREATMENT/CLEANING OF SUBSTRATE

The surface to be coated must be dry, clean, and free of grease and other contaminants. Ensure all substrates are thoroughly cleaned and dried at every step of the preparation process.



Clean the surface with 770 NORMAL / 771 FAST ANTISIL Degreaser.

Use 2 clothes wipe on, wipe off. Always wipe cleaner off the surface as long is wet, with a clean, dry cloth. Remove dust by air blowing and a tack cloth.

### PRODUCT APPLICATION



Shake well before using:  
2 - 3 min



Spray at a distance of  
20 - 30 cm, thinly applied  
coats



2 - 3 coats  
20 - 30 µm  
(0.8 - 1.2 mil)



5 min / 23°C (73°F)  
Flash off between coats



10 min / 23°C (73°F)



Overcoat with any HB  
BODY 1K and 2K Primer  
and Topcoat



After use turn bottle  
upside down and spray  
out a small quantity,  
for the cleaning of the  
nozzle

### SPECIFIC GRAVITY

0.85 ± 0.02 g/cm<sup>3</sup>

### SOLID CONTENT

12 ± 2% Weight

### VOC (2004/42/EC)

This is an aerosol product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 840g/L. 2004/42/IIIB(e)(840)840

### REMARKS

- Shake for 2 - 3 min after agitator ball has started to rattle.
- It is recommended to test on a similar surface for achieving the desired finishing result.
- Optimum operating temperature range 10 - 25°C (50 - 77°F).

**WARNING:** Do not use Etch Primers under any polyester system.

### STORAGE SHELF LIFE

Guaranteed shelf-life 36 months in unused original containers stored in a cool place (5 - 25°C) (41 - 77°F).



Always wear protective equipment



Follow the application instructions mentioned in this TDS

The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

DECEMBER 2025